



- (51) **International Patent Classification:**
C07F 15/00 (2006.01) *H05B 33/14* (2006.01)
C09K 11/06 (2006.01)
- (21) **International Application Number:**
PCT/CN2012/076252
- (22) **International Filing Date:**
30 May 2012 (30.05.2012)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
61/491,711 31 May 2011 (31.05.2011) US
- (71) **Applicant (for all designated States except US):** **THE UNIVERSITY OF HONG KONG** [CN/CN]; Pokfulam Road, Hong Kong (CN).
- (72) **Inventors; and**
- (75) **Inventors/Applicants (for US only):** **CHE, Chiming** [CN/CN]; Flat 5, 5/F, Block A Parkway Court, 4 Park Road, Hong Kong (CN). **LI, Kai** [CN/CN]; Flat A, 10/F, Block 1, Kong Chian Tower, No. 351 Des Voeus Road West, Hong Kong (CN).
- (74) **Agent:** **CHINA PATENT AGENT (HK) LTD.**; 22/F., Great Eagle Center, 23 Harbour Road, Hong Kong (CN).
- (81) **Designated States (unless otherwise indicated, for every kind of national protection available):** AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) **Designated States (unless otherwise indicated, for every kind of regional protection available):** ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— with international search report (Art. 21(3))

(54) **Title:** PHOSPHORESCENT MATERIAL, THEIR PREPARATIONS AND APPLICATIONS




Figure 6

(57) **Abstract:** The subject invention is directed to tetradentate *bis*-(NHC carbenes) alkylene ligand Pt(II) complexes, tetradentate *bis*-(NHC carbenes) alkylene ligands, and its ligand precursors, for preparation of the Pt(II) complexes. The Pt(II) complexes show a deep blue emission with an improved quantum efficiency and can be used for fabrication of OLEDs with an electroluminescence layer that comprise the *bis*-(NHC carbenes) alkylene ligand Pt(II) complexes.

PHOSPHORESCENT MATERIAL, THEIR PREPARATIONS AND APPLICATIONS

DESCRIPTION

5 CROSS-REFERENCE TO RELATED APPLICATION

This application claims the benefit of U.S. Provisional Application Serial No. 61/491,711, filed May 31, 2011, which is hereby incorporated by reference in its entirety including any tables, figures, or drawings.

10 FIELD OF THE INVENTION

The invention relates to a class of phosphorescent materials, their preparation methods and organic light emitting diodes (OLEDs) using these materials.

BACKGROUND OF THE INVENTION

15 The first organic light-emitting diode (OLED) was disclosed by Tang *et al.* (U.S. Patent 4,356,429) and Tang *et al.* (*Appl. Phys. Lett.* 1987, 51, 12, 913). Subsequently, device architecture and emissive materials for OLED applications have been intensively studied. OLEDs allow devices that are (1) ultra-thin; (2) self-emissive; (3) use low operating voltage with high efficiency; and (4) display high contrast and resolution.

20 Phosphorescent materials are the primary direction of emissive material development, because these OLED devices generate 25 % singlet and 75 % triplet excitons. Devices fabricated from phosphorescent materials generally display efficiencies that are higher than devices fabricated from fluorescent materials. Platinum complexes are a class of emissive materials that offer high emission quantum efficiency and good thermal stability. High performance OLEDs
25 have been formed using platinum(II) complexes. (Yan *et al.*, *Appl. Phys. Lett.* 2007, 91(6) 063508; Che *et al.*, *Chemistry-A European Journal* 2010, 16(1), 233)


Producing blue-emitting phosphorescent materials has proven to be challenging. However, high performance and long lifetime blue-emitting OLEDs have not been fabricated from platinum(II) complexes. To tune the emission color of platinum(II) complexes, the
30 appropriate conjugation length of the ligand is essential. Neutral blue-emitting Pt(II) complex

were prepared by coordinating two bidentate ligands to a Pt(II) center, resulting in the first blue-emitting Pt(II) complexes. (Brooks *et al.*, *Inorg. Chem.* 2002, 41, 3055; and Unger *et al.*, *Angew. Chem. Int. Ed.* 2010, 49, 10214) However, binding forces between these bidentate ligands and the platinum(II) center in these complexes are weaker than the binding forces of complexes containing one tetradentate ligand bound to a Pt(II). The devices that form these bis-bidentate ligand Pt(II) complexes display lifetimes and stabilities that are inferior to device tetradentate Pt(II) complexes. Ligand systems having more than two aryl groups, coupled by a non-conjugated unit, do not provide emission maxima less than 480 nm. (U.S. Patent No. 7,026,480, U.S. Patent No. 6,653,654). Blue-emitting materials have not been made from this type of tridentate or tetradentate ligands. Efforts directed to tetradentate blue-emitting Pt(II) materials where conjugation groups connect aryl groups of the ligands, have failed to generate complexes with emission maxima less than 480 nm. (U.S. Patent No. 7,361,415, U.S. Patent No. 7,691,495 and U.S. Published Patent Application 2007/0103060 A1)

N-heterocyclic carbenes (NHC) are strong σ -donors but poor π -acceptors. Using cyclometalated Pt(II) complexes, Meyer *et al.*, *Organometallics*, 2011, 30 (11), 2980 discloses Pt(II) complexes with shortened ligand π -conjugations, but does not report of the emission spectra.

BRIEF SUMMARY OF THE INVENTION

Embodiments of the invention are directed to blue phosphorescent platinum(II) complexes of dianionic tetradentate *bis*-(NHC carbene) ligand of structure II:



wherein R_1 - R_8 are, independently, hydrogen, fluoro, chloro, bromo, iodo, hydroxyl, alkyl, substituted alkyl, cycloalkyl, substituted cycloalkyl, aryl, substituted aryl, acyl, alkoxy, acyloxy, amino, nitro, acylamino, aralkyl, cyano, carboxyl, thio, styryl, aminocarbonyl, carbamoyl, aryloxycarbonyl, phenoxycarbonyl, or alkoxycarbonyl, and X is, independently, oxygen, nitrogen, sulphur, phosphorus, or selenium. Other embodiments of the invention are directed to the preparation of the tetradentate *bis*-(NHC carbene) ligands where at least one of R_1 - R_8 are not hydrogen, and OLEDs comprise Pt(II) complexes of tetradentate *bis*-(NHC carbene) ligands.

BRIEF DESCRIPTION OF THE DRAWINGS

10 Figure 1 shows a reaction scheme for the preparation of tetradentate *bis*-(NHC carbene) ligand precursors, according to an embodiment of the invention.

Figure 2 shows the structure of three exemplary tetradentate *bis*-(NHC carbene) ligand precursors, 1-3, according to an embodiment of the invention.

15 Figure 3 shows a reaction scheme for the conversion of a tetradentate *bis*-(NHC carbene) ligand precursor to a tetradentate *bis*-(NHC carbene) ligand Pt(II) complex, according to an embodiment of the invention.

Figure 4 shows the structure of three exemplary tetradentate *bis*-(NHC carbene) ligand Pt(II) complexes, 4-6, according to an embodiment of the invention.

20 Figure 5 shows the X-ray crystal structure of complex 5, according to an embodiment of the invention: a) as a perspective view with thermal ellipsoids in 50% probability and hydrogen atoms and solvated molecules omitted for clarity; and b) the packing diagram viewed along *c*-axis.

25 Figure 6 shows absorption and emission spectra of 4, with absorption below 382 and emission above 382, for a dichloromethane-DMF solution (19:1,v/v), THF-DMF solution (19:1,v/v) (blue shifted), and a film of 4 in poly(methylmethacrylate) (1 wt %) (emission only and further blue shifted), according to an embodiment of the invention.

30 Figure 7 shows absorption and emission spectra of 5, with absorption below 382 and emission above 382, for a dichloromethane-DMF solution (19:1,v/v), THF-DMF solution (19:1,v/v) (blue shifted), and a film of 5 in poly(methylmethacrylate) (1 wt %) (emission only and further blue shifted), according to an embodiment of the invention.

Figure 8 shows absorption and emission spectra of 6, with absorption below 382 and emission above 382, for a THF-DMF solution (19:1,v/v) (blue shifted), and a film of 6 in poly(methylmethacrylate) (1 wt %) (emission only and blue shifted), according to an embodiment of the invention.

5 Figure 9 shows thermal gravimetric plots for complexes 4-7, according to an embodiment of the invention.


Figure 10 shows the chemical structure of NPB, 2-TNATA, and TPBi, which are used for the construction of an exemplary OLED with an emissive layer comprising 5, according to an embodiment of the invention.

10 Figure 11 shows an electroluminescence spectrum for the exemplary OLED with an emissive layer comprising 5, according to an embodiment of the invention.

Figure 12 shows a JVB cure for the exemplary OLED with an emissive layer comprising 5, according to an embodiment of the invention.


15 DETAILED DISCLOSURE OF THE INVENTION

Embodiments of the invention are directed to tetradentate ligands comprising a *bis*-(NHC carbenes) alkylene, as shown in the *bis*-anion-*bis*-carbene form in structure I:



20 wherein R₁-R₈ are, independently, hydrogen, fluoro, chloro, bromo, iodo, hydroxyl, alkyl, substituted alkyl, cycloalkyl, substituted cycloalkyl, aryl, substituted aryl, acyl, alkoxy, acyloxy, amino, nitro, acylamino, aralkyl, cyano, carboxyl, thio, styryl, aminocarbonyl, carbamoyl, aryloxycarbonyl, phenoxycarbonyl, or alkoxycarbonyl; and wherein at least one of R₁-R₈ is not hydrogen; and X is O, NR₉, S, PR₉, or Se, where R₉ is H or alkyl. In an embodiment of the
 25 invention, R₆ is not hydrogen. In an embodiment of the invention, R₈ is not hydrogen.


Embodiments of the invention are directed to stable blue-emitting platinum(II) complexes prepared from ligands comprising *bis*-(NHC carbenes) where the tetradentate ligand I's electron donor substituents, X, are in anions in a Pt complex of structure II:



5

wherein R₁-R₇ are, independently, hydrogen, fluoro, chloro, bromo, iodo, hydroxyl, alkyl, substituted alkyl, cycloalkyl, substituted cycloalkyl, aryl, substituted aryl, acyl, alkoxy, acyloxy, amino, nitro, acylamino, aralkyl, cyano, carboxyl, thio, styryl, aminocarbonyl, carbamoyl, aryloxycarbonyl, phenoxy carbonyl, or alkoxy carbonyl; wherein at least one of R₁-R₈ is not hydrogen; and X is O, NR₉, S, PR₉, or Se, where R₉ is H or alkyl. In an embodiment of the invention, R₆ is not hydrogen. In an embodiment of the invention, R₈ is not hydrogen

In an embodiment of the invention, the tetradentate ligand precursor is in the protonated form:



15 wherein R₁-R₇ are, independently, hydrogen, fluoro, chloro, bromo, iodo, hydroxyl, alkyl, substituted alkyl, cycloalkyl, substituted cycloalkyl, aryl, substituted aryl, acyl, alkoxy, acyloxy, amino, nitro, acylamino, aralkyl, cyano, carboxyl, thio, styryl, aminocarbonyl, carbamoyl, aryloxycarbonyl, phenoxy carbonyl, or alkoxy carbonyl; wherein at least one of R₁-R₈ is not hydrogen; X is O, NR₉, S, PR₉, or Se, where R₉ is H or alkyl; and A⁻ is chloride, bromide, iodide, 20 tosylate, brosylate, triflate, or other anion of low nucleophilicity. In an embodiment of the

invention, R₆ is not hydrogen. In an embodiment of the invention, R₈ is not hydrogen.

Tetradentate ligand precursors III can be prepared by a series of reactions depicted in Figure 1, where A⁻ is Br⁻. Synthesis occurs through reaction of an X protected *o*-halo substituted phenol, thiol, selenol, aniline, *N*-alkylaniline, phenylphosphane, or *P*-alkyl phenylphosphane, with imidazole, either unsubstituted, 4-substituted, or 4,5-disubstituted. The resulting *N*-aryl substituted imidazoles di-substitute a *gem*-dihaloalkane, or its functional equivalent towards nucleophilic substitution, as can be appreciated by one skilled in the art. The protected precursor is one where H of the XH is replaced with a protecting group that can be replaced with hydrogen, for example a methyl group. The reaction results in an X protected *bis*-(NHC carbenes) alkylene precursor, where upon deprotection, the *bis*-(NHC carbenes) alkylene ligand is provided as a precursor in a tetra-protonated form. Exemplary tetra-protonated *bis*-(NHC carbenes) alkylene ligand precursors, according to an embodiment of the invention, are shown in Figure 2.

Exemplary tetradentate *bis*-(NHC carbenes) alkylene ligand Pt(II) complexes, according to an embodiment of the invention, are shown in Figure 4. In an embodiment of the invention, the tetradentate *bis*-(NHC carbenes) alkylene ligand Pt(II) complex displays a vibronically structured absorption band, with a peak maximum at about 350 nm and molar extinction coefficient of about $1 \times 10^4 \text{ M}^{-1} \text{ cm}^{-1}$, and displays, in solution, a structure-less emission having λ_{max} at about 460 nm with a quantum yield, ϕ , in excess of 5 % and a lifetime, τ , in excess of 1.5 μs . In embodiments of the invention, the blue emission of the *bis*-(NHC carbenes) alkylene ligand Pt(II) complex has a blue emission in dilute solution with a λ_{max} less than 470 nm and a quantum yield greater than 5 percent. The *bis*-(NHC carbenes) alkylene ligand Pt(II) complex is a neutral square-planar Pt(II) complex, that is rigid and thermal stable, wherein thermal decomposition occurs at temperatures above 280 °C.

In an embodiment of the invention, the tetra-protonated *bis*-(NHC carbenes) alkylene ligand precursor is combined with a Pt(II) salt to form a tetradentate *bis*-(NHC carbenes) alkylene ligand Pt(II) complex, as illustrated in Figure 3. The Pt(II) salt can be a solvated or unsolvated platinum halide or its equivalent. For example the dimethylsulfoxide solvated PtCl₂, Pt(DMSO)₂Cl₂ can be used. The complexation is carried out in solution in the presence of a proton acceptor, such as an amine. In an embodiment of the invention the proton acceptor is a

tertiary amine, such as, but not limited to, trimethylamine, triethylamine, pyridine, *N,N,N,N*-tetramethylethylenediamine, or 1,4-dimethylpiperazine.

According to an embodiment of the invention, tetradentate *bis*-(NHC carbenes) alkylene ligand Pt(II) complexes are dispersed and immobilized in an inert polymer matrix, for example, but not limited to, poly(methyl methacrylate) (PMMA), to form a highly emissive film in the blue spectral region at a complex to polymer weight ratio of 1% or more. Absolute emission quantum yields for these films are around 30%, as measured with an integrate sphere method at room temperature. Emission maxima of the films can be blue-shifted by up to 10 nm from that for the *bis*-(NHC carbenes) alkylene ligand Pt(II) complexes in solution, suggesting a solid-
10 solution state in the polymer dispersions. The films exhibit emission with chromaticity, as indicated by Commission Internationale de L'Eclairage coordinates, of $CIE_{x,y} < 0.2$ and $CIE_{x+y} < 0.3$. For example, complex 4, shown in Figure 4, displays $CIE_{x,y}$ of (0.15, 0.10), which is nearly that considered to be an ideal deep blue, where $CIE_{x,y}$ of (0.14, 0.10).

All patents and publications referred to or cited herein are incorporated by reference in
15 their entirety, including all figures and tables, to the extent they are not inconsistent with the explicit teachings of this specification.

Following are examples that illustrate procedures for practicing the invention. These examples should not be construed as limiting. All percentages are by weight and all solvent mixture proportions are by volume unless otherwise noted.

20

MATERIALS AND METHODS

All starting materials were used as received from commercial sources. The solvents used for photophysical measurements were of HPLC grade. Elemental analyses were performed by the Institute of Chemistry at the Chinese Academy of Sciences, Beijing. Fast atom bombardment
25 (FAB) mass spectra were obtained on a Finnigan Mat 95 mass spectrometer. ^1H (300 MHz or 400 MHz) NMR spectra were recorded on DPX300 and Avance400 Bruker FT-NMR spectrometers. UV-Vis spectra were recorded on a Perkin-Elmer Lambda 19 UV/vis spectrophotometer. Steady-state emission and excitation spectra at 298 K and Photoluminescence of films on quartz substrate were obtained on a Spex 1681 Fluorolog-2 Model
30 F111 spectrophotometer equipped with a Hamamatsu R928 PMT detector. All solutions for

photophysical measurements, except stated otherwise, were degassed in a high-vacuum line with at least four freeze-pump-thaw cycles. Emission lifetimes were measured with a Quanta-Ray Q-switch DCR-3 Nd:YAG pulsed laser system. Emission quantum yields were measured using a degassed acetonitrile solution of [Ru(bpy)₃](PF₆)₂ (bpy = 2,2'-bipyridine) as the standard ($\phi_r =$
5 0.062) and calculated by $\phi_s = \phi_r (B_r/B_s)(n_s/n_r)^2 (D_s/D_r)$, where the subscripts s and r refer to the sample and reference standard solution, respectively, n is the refractive index of the solvents, D is the integrated intensity, and ϕ is the luminescence quantum yield. The quantity B is calculated by $B = 1 - 10^{-AL}$, where A is the absorbance at the excitation wavelength and L is the optical path length. Errors for wavelength values (1 nm) and ϕ (10%) are estimated.

10 4-Methyl-2-bromoanisole and 4-(tert-butyl)-2-bromoanisole were prepared from 4-Methyl-2-bromophenol and 4-(tert-butyl)-2-bromophenol by reaction with MeI in the presence of K₂CO₃ following literature procedure. (Lygo, *Tetrahedron Lett.*, 1999, 40, 1389) 4-methyl-2-bromoanisole: 84% ¹H-NMR (400 MHz, CDCl₃) δ (ppm) 7.36 (d, J=2.1 Hz, 1H), 7.05 (dd, J=8.3 Hz, 2.1 Hz, 1H), 6.79 (d, J=8.3 Hz, 1H), 3.86 (s, 3H), 2.28 (s, 3H) 4-(tert-butyl)-2-bromoanisole: ¹H-NMR (300 MHz, CDCl₃) δ (ppm) 7.54 (d, J=2.2 Hz, 1H), 7.27 (dd, J=8.6 Hz,
15 2.2 Hz, 1H), 6.83 (d, J=8.6 Hz, 1H), 3.87 (s, 3H), 1.28 (s, 9H).

2-(1*H*-imidazol-1-yl)anisole: To a degassed DMSO (20 mL) solution of imidazole (1.0 g, 15 mmol) was added 2-bromoanisole (1.25 mL, 10 mmol), KOH (1.12 g, 20 mmol) and Cu₂O (280 mg, 2 mmol) under nitrogen. The resulting mixture was stirred at 140 °C for 24 hrs under N₂.
20 After cooling to room temperature, the mixture was poured into ethylacetate (EA) (50 mL) and filtered. The filtrate was washed with water (50 mL \times 3) and dried over anhydrous magnesium sulfate. After rotary evaporation, the crude oil was purified via column chromatography on silica gel with eluent of EA/MeOH (9/1, v/v), affording a light yellow liquid (50%). ¹H-NMR (400 MHz, CDCl₃) δ (ppm) 7.79 (s, 1H), 7.36 (t, J=7.8 Hz, 1H), 7.28 (d, J=7.8 Hz, 1H), 7.21 (s, 1H),
25 7.17 (s, 1H), 7.05 (m, 2H), 3.85 (s, 3H).

4-fluoro-2-(1*H*-imidazol-1-yl)anisole: To a degassed DMSO (20 mL) solution of imidazole (1.0 g, 15 mmol) was added 4-fluoro-2-bromoanisole (1.25 mL, 10 mmol), KOH (1.12 g, 20 mmol) and Cu₂O (280 mg, 2 mmol) under nitrogen. The resulting mixture was stirred at 140 °C for 24 hrs under N₂. After cooling to room temperature, the mixture was poured into ethylacetate (EA)
30 (50 mL) and filtered. The filtrate was washed with water (50 mL \times 3) and dried over anhydrous

magnesium sulfate. After rotary evaporation, the crude oil was purified via column chromatography on silica gel with eluent of EA/MeOH (9/1, v/v), affording a light yellow liquid (47%). ¹H-NMR (400 MHz, CDCl₃) δ(ppm) 7.82 (s, 1H), 7.21 (m, 1H), 7.17 (m, 1H), 7.07 (m, 2H), 7.00 (m, 1H), 3.84 (s, 3H).

5 4-methyl-2-(1*H*-imidazol-1-yl)anisole: To a degassed DMSO (20 mL) solution of imidazole (1.0 g, 15 mmol) was added 4-methyl-2-bromoanisole (1.25 mL, 10 mmol), KOH (1.12 g, 20 mmol) and Cu₂O (280 mg, 2 mmol) under nitrogen. The resulting mixture was stirred at 140 °C for 24 hrs under N₂. After cooling to room temperature, the mixture was poured into ethylacetate (EA) (50 mL) and filtered. The filtrate was washed with water (50 mL ×3) and dried over
10 anhydrous magnesium sulfate. After rotary evaporation, the crude oil was purified via column chromatography on silica gel with eluent of EA/MeOH (9/1, v/v), affording a light yellow solid (57%). ¹H-NMR (300 MHz, CDCl₃) δ(ppm) 7.78 (s, 1H), 7.16 (m, 3H), 7.09 (d, J=1.8 Hz, 1H), 6.94 (d, J=8.4 Hz, 1H), 3.81 (s, 3H), 2.33 (s, 3H).

4-*t*-butyl-2-(1*H*-imidazol-1-yl)anisole: To a degassed DMSO (20 mL) solution of imidazole
15 (1.0 g, 15 mmol) was added 4-methyl-2-bromoanisole (1.25 mL, 10 mmol), KOH (1.12 g, 20 mmol) and Cu₂O (280 mg, 2 mmol) under nitrogen. The resulting mixture was stirred at 140 °C for 24 hrs under N₂. After cooling to room temperature, the mixture was poured into ethylacetate (EA) (50 mL) and filtered. The filtrate was washed with water (50 mL ×3) and dried over anhydrous magnesium sulfate. After rotary evaporation, the crude oil was purified via column
20 chromatography on silica gel with eluent of EA/MeOH (9/1, v/v), affording a light yellow oil with yield of 47%. ¹H-NMR (400 MHz, CDCl₃) δ(ppm) 7.77 (s, 1H), 7.37 (dd, J₁= 8.6 Hz, J₂=2.4 Hz, 1H), 7.27 (d, J=2.4 Hz, 1H), 7.21 (1H), 7.17 (1H), 6.99 (d, J=8.6 Hz, 1H), 3.82 (s, 3H), 1.32 (s, 9H).

1,1'-*bis*[(2-methoxyphenyl)-1*H*-imidazolium]-3,3'-methanediyl dibromide: A solution of 2-
25 (1*H*-imidazol-1-yl)anisole (0.82 g, 4.7 mmol) and dibromomethane (1 mL, 14 mmol) in THF (5 mL) was refluxed at 110 °C for 48 hrs. After cooling to room temperature, the resulting white precipitate was collected by filtration with suction, washed with THF, and air-dried to yield 0.9g of solids (73%). ¹H-NMR (400 MHz, DMSO-*d*₆) δ(ppm) 10.01 (s, 2H), 8.30 (m, 2H), 8.22 (m, 2H), 7.64 (m, 4H), 7.41 (d, J=8.3 Hz, 2H), 7.22 (t, J=7.7 Hz, 2H), 6.90 (s, 2H), 3.90 (s, 6H).

1,1'-bis[(4-fluoro-2-methoxyphenyl)-1*H*-imidazolium]-3,3'-methanediyl dibromide: A solution of 4-fluoro-2-(1*H*-imidazol-1-yl)anisole (0.90 g, 4.7 mmol) and dibromomethane (1 mL, 14 mmol) in THF (5 mL) was refluxed at 110 °C for 48 hrs. After cooling to room temperature, the resulting white precipitate was collected by filtration with suction, washed with THF, and air-dried to yield a white solid with yield of 70%. ¹H-NMR (400 MHz, MeOD) δ(ppm) 8.33 (d, J=2.1 Hz, 2H), 8.11 (d, J=2.1 Hz, 2H), 7.66 (m, 2H), 7.40 (m, 4H), 7.11 (s, 2H), 3.98 (s, 6H). Note: the imidazole NCHN signal do not appeared in MeOD solvent.

1,1'-bis[(4-methyl-2-methoxyphenyl)-1*H*-imidazolium]-3,3'-methanediyl dibromide: A solution of 4-methyl-2-(1*H*-imidazol-1-yl)anisole (0.88 g, 4.7 mmol) and dibromomethane (1 mL, 14 mmol) in THF (5 mL) was refluxed at 110 °C for 48 hrs. After cooling to room temperature, the resulting white precipitate was collected by filtration with suction, washed with THF, and air-dried to yield a white solid with yield of 70%. ¹H-NMR (300 MHz, DMSO-d₆) δ(ppm) 9.93 (s, 2H), 8.26 (m, 2H), 8.20 (m, 2H), 7.47 (d, J=1.6 Hz, 2H), 7.44 (dd, J₁=8.6 Hz, J₂=1.6 Hz, 2H), 7.31 (d, J=8.6 Hz, 2H), 6.86 (s, 2H), 3.88 (s, 3H), 2.33 (s, 3H).

1,1'-bis[(4-*t*-butyl-2-methoxyphenyl)-1*H*-imidazolium]-3,3'-methanediyl dibromide: A solution of 4-*t*-butyl-2-(1*H*-imidazol-1-yl)anisole (1.08 g, 4.7 mmol) and dibromomethane (1 mL, 14 mmol) in THF (5 mL) was refluxed at 110 °C for 48 hrs. After cooling to room temperature, the resulting white precipitate was collected by filtration with suction, washed with THF, and air-dried to yield a white solid with yield of 74%. ¹H-NMR (400 MHz, DMSO-d₆) δ(ppm) 10.00 (s, 2H), 8.31 (m, 2H), 8.24 (m, 2H), 7.64 (m, 4H), 7.33 (d, J=8.8 Hz, 2H), 6.89 (s, 2H), 3.89 (s, 3H), 1.28 (s, 18H).

1,1'-bis[(2-hydroxyphenyl)-1*H*-imidazolium]-3,3'-methanediyl dibromide: A solution of 1,1'-bis[(2-methoxyphenyl)-1*H*-imidazolium]-3,3'-methanediyl dibromide (0.81g, 1.55 mmol) in HBr (48 wt. % aq. 6.5 mL)/HOAc (6.5 mL) was heated to reflux at 120 °C for 48 hrs. After reaction, the mixture was rotary evaporated. Acetone was added to the residue to induce precipitation of brown solids, which were collected by filtration and washed with EA. After reprecipitation from DMF/EA, a white solid was obtained (0.52 g, 68%). ¹H-NMR (400 MHz, DMSO-d₆) δ(ppm) 11.08 (br s, 2H), 9.99 (s, 2H), 8.29 (s, 2H), 8.22 (s, 2H), 7.57 (d, J=7.86 Hz, 2H), 7.44 (t, J=7.77 Hz, 2H), 7.19 (d, J= 8.13 Hz, 2H), 7.06 (t, J= 7.58 Hz, 2H), 6.90 (s, 2H).

1,1'-bis[(4-fluoro-2-hydroxyphenyl)-1*H*-imidazolium]-3,3'-methanediyl dibromide (1): A solution of 1,1'-bis[(4-fluoro-2-methoxyphenyl)-1*H*-imidazolium]-3,3'-methanediyl dibromide (0.87g, 1.55 mmol) in HBr (48 wt. % aq. 6.5 mL)/HOAc (6.5 mL) was heated to reflux at 120 °C for 48 hrs. After reaction, the mixture was rotary evaporated. Acetone was added to the residue to induce precipitation of brown solids, which were collected by filtration and washed with EA. After reprecipitation from MeOH/EA, a white solid was obtained with yield of 84% ¹H-NMR (300 MHz, MeOD) δ(ppm) 9.97 (im NCHN, s, active), 8.23(d, J=2.0 Hz, 2H), 8.13 (d, J=2.0 Hz, 2H), 7.52 (dd, J₁=8.4 Hz, J₂=3.0 Hz, 2H), 7.26 (td, J₁=9.0 Hz, J₂=3.0 Hz, 2H), 7.14 (dd, J₁=9.0 Hz, J₂=4.8 Hz, 2H), 7.00 (s, 2H).

1,1'-bis[(4-methyl-2-hydroxyphenyl)-1*H*-imidazolium]-3,3'-methanediyl dibromide (2): A solution of 1,1'-bis[(4-methyl-2-methoxyphenyl)-1*H*-imidazolium]-3,3'-methanediyl dibromide (0.85g, 1.55 mmol) in HBr (48 wt. % aq. 6.5 mL)/HOAc (6.5 mL) was heated to reflux at 120 °C for 48 hrs. After reaction, the mixture was rotary evaporated. Acetone was added to the residue to induce precipitation of brown solids, which were collected by filtration and washed with EA. After reprecipitation from MeOH/EA, a white solid was obtained with yield of 65% ¹H-NMR (300 MHz, DMSO-d₆) δ(ppm) 10.82 (br s, 2H), 9.96 (s, 2H), 8.28 (m, 2H), 8.20 (m, 2H), 7.39 (d, J=1.6 Hz, 2H), 7.25 (dd, J₁=8.4 Hz, J₂=1.6 Hz, 2H), 7.08 (d, J=8.4 Hz, 2H), 6.88 (s, 2H), 2.28 (s, 6H). (300 MHz, MeOD) δ(ppm) 9.91 (im NCHN, s, 2H), 8.20 (m, 2H), 8.09 (m, 2H), 7.43 (d, J=1.6 Hz, 2H), 7.28 (dd, J₁=8.4 Hz, J₂=1.6 Hz, 2H), 7.03 (d, J=8.4 Hz, 2H), 6.98 (s, 2H), 2.35 (s, 6H).

1,1'-bis[(4-*t*-butyl-2-hydroxyphenyl)-1*H*-imidazolium]-3,3'-methanediyl dibromide (3): A solution of 1,1'-bis[(4-*t*-butyl-2-methoxyphenyl)-1*H*-imidazolium]-3,3'-methanediyl dibromide (0.98g, 1.55 mmol) in HBr (48 wt. % aq. 6.5 mL)/HOAc (6.5 mL) was heated to reflux at 120 °C for 48 hrs. After reaction, the mixture was rotary evaporated. Acetone was added to the residue to induce precipitation of brown solids, which were collected by filtration and washed with EA. After reprecipitation from DMF/EA, a white solid was obtained with yield of 62%. ¹H-NMR (400 MHz, DMSO) δ(ppm) 10.85 (s, 2H), 9.91 (s, 2H), 8.24 (m, 4H), 7.48 (m, 4H), 7.11 (d, J=8.4 Hz), 6.84 (s, 2H), 1.29 (s, 18H).

Bis[3,3'-(2-phenoxy)-1*H*-imidazolium-2,2'-diylidene]-methane-1,1'-diyl-platinum(II) (7):

A mixture of 1,1'-bis[(2-hydroxyphenyl)-1*H*-imidazolium]-3,3'-methanediyl dibromide (193 mg,

0.39 mmol), Pt(DMSO)₂Cl₂ (164 mg, 0.39 mmol) and Et₃N (0.325 mL, 6 eq.) in EtOH (20 mL) was heated to 80 °C for 6 hrs. After completion of reaction, the mixture was cooled to room temperature, collected by centrifugation, washed with ethanol, ether and was dried under vacuum, affording pale yellow solids (60%). ¹H-NMR (400 MHz, DMSO-d₆) δ(ppm) 8.34 (d, J=2.3 Hz, 2H), 7.71 (d, J=2.3 Hz, 2H), 7.69 (d, J=8.35 Hz, 2H), 7.06 (t, J=7.65 Hz, 2H), 6.92 (d, J=8.27 Hz, 2H), 6.57 (t, J=7.57 Hz, 2H), 6.31 (s, 2H) FAB-MS: 526.0 [M+H]⁺. Anal. Calcd. For C₁₉H₁₄N₄O₂Pt·H₂O: C, 41.99; H, 2.97; N, 10.31. Found: C, 42.06; H, 2.88; N, 9.99.

Bis[3,3'-(4-fluoro-2-phenoxy)-1H-imidazolium-2,2'-diylidene]-methane-1,1'-diyl-

platinum(II) (4): A mixture of 1 (207 mg, 0.39 mmol), Pt(DMSO)₂Cl₂ (164 mg, 0.39 mmol) and Et₃N (0.325 mL, 6 eq.) in EtOH (20 mL) was heated to 80 °C for 6 hrs. After completion of reaction, the mixture was cooled to room temperature, collected by centrifugation, washed with ethanol, ether and was dried under vacuum, affording white solids with yield of 49%. ¹H-NMR (400 MHz, DMSO-d₆) δ(ppm) 8.34 (d, J=1.8 Hz, 2H), 7.72 (d, J=1.8 Hz, 2H), 7.66 (d, J=10.5 Hz, 2H), 6.90 (m, 4H), 6.32 (s, 2H) FAB-MS: 561.0 [M+H]⁺. Anal. Calcd. For C₁₉H₁₂N₄O₂Pt·H₂O: C, 39.38; H, 2.44; N, 9.67. Found: C, 38.77; H, 2.40; N, 9.35.

Bis[3,3'-(4-methyl-2-phenoxy)-1H-imidazolium-2,2'-diylidene]-methane-1,1'-diyl-

platinum(II) (5): A mixture of 2 (204 mg, 0.39 mmol), Pt(DMSO)₂Cl₂ (164 mg, 0.39 mmol) and Et₃N (0.325 mL, 6 eq.) in EtOH (20 mL) was heated to 80 °C for 6 hrs. After completion of reaction, the mixture was cooled to room temperature, collected by centrifugation, washed with ethanol, ether and was dried under vacuum, affording white solids with yield of 56%. ¹H-NMR (300 MHz, DMSO-d₆) δ(ppm) 8.31 (d, J=2.1 Hz, 2H), 7.69 (d, J=2.1 Hz, 2H), 7.51 (s, 2H), 6.87 (d, J=8.2 Hz, 2H), 6.80 (d, J=8.2 Hz, 2H), 6.29 (s, 2H), 2.25 (s, 6H) FAB-MS: 553.0 [M+H]⁺. Anal. Calcd. For C₂₁H₁₈N₄O₂Pt·CH₂Cl₂: C, 41.39; H, 3.16; N, 8.78. Found: C, 41.38; H, 3.22; N, 8.82.

A single-crystal of 5 suitable for X-ray diffraction analysis was obtained from a dilute solution in dichloromethane upon slow evaporation of the solvent in the presence of air. The complex crystallized into an orthorhombic space group, as indicated in Table 1, below. As can be seen in Figure 5a, Complex 5 has a C₂-symmetry along the Pt1-C11 axis. The four bond angles around Pt(II) are within 90±2°, indicating a square-planar coordination geometry with a negligible strain in the tetradentate ligand accommodating the Pt(II) ion. The Pt-C(NHC)

distances of 1.93 Å are shorter than those found in tetra(NHC)-Pt(II) (2.03 Å) and bis(NHC)-Pt(II) acetylide (1.98 Å) complexes, indicating strong Pt–C(NHC) bonding interactions. The Pt–O(phenolate) distances of 2.05 Å are slightly longer than those found in Salphen-Pt(II) (1.99 Å) and (N₂O₂)-Pt(II) (1.98 Å) complexes, probably due to weak Pt–O(phenolate) bonds induced by the strong *trans*-effect of the NHC moieties. The molecules of 5 adopt a bent framework due to the non-conjugated C11 methylene linker between the two NHC moieties, and these bent molecules stack into infinite columns in a head-to-tail cofacial manner with intermolecular π - π distances of 3.5 Å along *a*-axis, as shown in Figure 5b. A solvated water molecule is hydrogen-bonded to the two phenolate oxygen atoms of a complex molecule. Disordered solvating dichloromethane molecules are located in the channels between the columns formed by the stacked 5 molecules.

Table 1. Crystal Data of complex 3

formula	C ₂₂ H ₂₂ Cl ₂ N ₄ O ₃ Pt
fw	656.43
color	Colorless
crystal size	0.1×0.04×0.02
crystal system	Orthorhombic
space group	<i>Pnma</i>
<i>a</i> , Å	6.7618(2)
<i>b</i> , Å	24.1817(7)
<i>c</i> , Å	13.4445(4)
α , deg	90
β , deg	90
γ , deg	90
<i>V</i> , Å ³	2198.33
<i>Z</i>	4
<i>D_c</i> , g cm ⁻³	1.983
μ , cm ⁻¹	14.461
<i>F</i> (000)	1272
2 θ _{max} , deg	130.81
no. unique data	1872
no. obsd. data	
GOF	1.191
for <i>I</i> > 2 σ (<i>I</i>)	
no. variables	155
<i>R</i> ^a	0.0517
<i>R_w</i> ^b	0.0968
residual ρ , e Å ⁻³	1.364, -2.386

$${}^a R = \frac{\sum ||F_o| - |F_c||}{\sum |F_o|}, {}^b R_w = \left[\frac{\sum w (|F_o| - |F_c|)^2}{\sum w |F_o|^2} \right]^{1/2}.$$

Bis[3,3'-(4-*t*-butyl-2-phenoxide)-1H-imidazolium-2,2'-diylidene]-methane-1,1'-diyl-
platinum(II) (6): A mixture of 3 (237 mg, 0.39 mmol), Pt(DMSO)₂Cl₂ (164 mg, 0.39 mmol) and
5 Et₃N (0.325 mL, 6 eq.) in EtOH (20 mL) was heated to 80 °C for 6 hrs. After completion of
reaction, the mixture was cooled to room temperature, collected by centrifugation, washed with
ethanol, ether and was dried under vacuum, affording white solids with yield of 58%. ¹H-NMR
(400 MHz, DMSO-*d*₆) δ(ppm) 8.42 (d, 2.3 Hz, 2H), 7.71 (d, 2.3 Hz, 2H), 7.52 (d, J=2.3 Hz, 2H),
7.08 (dd, J₁= 8.6 Hz, J₂=2.3 Hz, 2H), 6.83 (d, J=8.6 Hz, 2H), 6.30 (s, 2H), 1.29 (s, 18H) FAB-
10 MS: 638.2 [M+H]⁺. Anal. Calcd. For C₂₇H₃₀N₄O₂Pt·H₂O: C, 49.46; H, 4.92; N, 8.55. Found: C,
49.36; H, 4.64; N, 8.46.

Absorption and emission spectra were acquired for complexes 4-7, as summarized in
Table 2, below, solution measurements were performed using THF-DMF (19:1, v/v) solutions.
All of the complexes show a vibronically structured absorption band with peak maxima at about
15 350 nm and molar extinction coefficients of about 1×10⁴ M⁻¹cm⁻¹. In solution, complexes 5 and
6 display structure-less emissions centered at around 460 nm with quantum yields of 8% and
lifetimes of 1.8 μs, which is significantly greater than that for 7, the complex from an
unsubstituted ligand. A blue-shifted emission maximum at 443 nm with a high quantum yield of
18% and long lifetime of 3.5 μs was observed in solution for complex 4 with an electron-
20 drawing fluoride group *para* to the phenolate oxygen. A red-shift of 5 nm for the emission
maxima for 4-7 was observed upon changing solvent from THF-DMF to dichloromethane-DMF
(19:1,v/v). Representative adsorption and emission spectra for 4-6 are shown in Figures 6-8
respectively.

Complexes 4-7 are highly emissive in the blue spectral region when measured in films
25 prepared by the dispersion of a complex in an inert polymer matrix, poly(methyl methacrylate)
(PMMA) in these exemplary examples, at a complex to polymer weight ratio as low as 1%.
Absolute emission quantum yields for these solid films, measured by an integrate sphere method,
were observed to be approximately 30%, within experimental error, at room temperature for 4-7
with emission maxima blue-shifted by 10 nm from that recorded for the complexes in THF-DMF
30 solution, which suggests a solid-solution state within the film. All of the films exhibit emission

with a chromaticity of $CIE_{x,y} < 0.2$ ($CIE_{x,y}$ = Commission Internationale de L'Eclairage coordinates) and $CIE_{x+y} < 0.3$, and particularly, films of complex 4 gave $CIE_{x,y}$ at (0.15, 0.10), being close to an ideal deep blue with $CIE_{x,y}$ at (0.14, 0.10).

Table 2 Photophysical data of complexes 4-7.

	Absorption ^[a]	Emission ^[a]	Emission ^[b]
	λ_{max} in nm (ϵ in $M^{-1}cm^{-1}$)	λ_{max} (nm); τ (μs); ϕ (%)	λ_{max} / nm; ϕ
4	286 (8.5), 310 (9.7), 353 (10.4), 365 (10.5)	443, 459; 3.5; 18%	434, 451; 26%
5	284 (10.0), 308 (9.4), 351 (9.7), 362 (9.7)	460; 1.8; 7%	448; 24%
6	282 (11.5), 308 (10.5), 352 (12.3), 363 (12.7)	461; 1.8; 8%	449; 26%
7	277 (8.4), 302 (7.3), 342 (7.1), 353 (7.1)	457; 0.5; 3%	443; 29%

- 5 [a] Recorded in degassed THF-DMF (19:1, v/v) solutions with a concentration of $\sim 2 \times 10^{-5}$ M, absorption at about 305 is a shoulder, and λ_{ex} for emissions is 350 nm. [b] Recorded in 1% PMMA film and λ_{ex} for emissions is 350 nm.

Decomposition temperatures of 4-6 under a nitrogen atmosphere are 410, 390, and 400
 10 °C, respectively, as determined by thermogravimetric analyses, as shown in Figure 9. Complexes 4-6 meet the prerequisite for thermal deposition of these complexes in OLED fabrications and exceeds that of unsubstituted complex 7 which decomposed beginning at 250 °C.

Complex 6 was used as phosphorescent dopant in a blue OLED. The device
 15 configuration is ITO / 2-TNATA (40 nm) / NPB (20 nm) / DP4-Pt 3% (30 nm) / TPBi (40 nm) / LiF (0.5 nm) / Al (100 nm). 2-TNATA, NPB and TPBi were used as hole-injection layer (HIL), hole-transporting layer (HTL) and electron-transporting layer (ETL), respectively. The host DP4 was obtained from Aglaia Tech. Beijing, China, and its chemical structure cannot be revealed due to patent consideration. All materials were thermal-deposited in high vacuum in succession
 20 without breaking the vacuum. After finishing the whole deposition, the device was encapsulated with glass cap and tested at ambient conditions. The electroluminescence was recorded by a PR650-spectrometer and K2400 as the voltage source.


An OLED was fabricated using 6, which was vacuum-deposited as a dopant into the emitting layer of an OLED with a configuration of ITO / 2-TNATA (40 nm) / NPB (20 nm) / DP4-Complex 102 (30 nm) / TPBi (40 nm) / LiF (0.5 nm) / Al (100 nm). 2-TNATA, NPB and TPBi, whose structures are shown in Figure 10, were used as hole-injection, hole-transporting and electron-transporting layer, respectively. Complex 6 was co-deposited with a broad-gap host (DP4, provided by Aglaia Tech., Beijing, China) at a 3 wt% doping level. The electroluminescence spectrum and JVB curve of the device are illustrated in Figures 11 and 12, respectively. A maximum brightness of 1200 cd/m² was recorded at a driving voltage of 15 V. The chromaticity of this device at 11 V is CIE_{x,y} (0.16, 0.16), falling well into the blue spectral region. A peak luminous efficiency of 0.5 cd/A was recorded at 11 V.

It should be understood that the examples and embodiments described herein are for illustrative purposes only and that various modifications or changes in light thereof will be suggested to persons skilled in the art and are to be included within the spirit and purview of this application and the scope of the appended claims. In addition, any elements or limitations of any invention or embodiment thereof disclosed herein can be combined with any and/or all other elements or limitations (individually or in any combination) or any other invention or embodiment thereof disclosed herein, and all such combinations are contemplated with the scope of the invention without limitation thereto.

CLAIMS

We claim:

1. A tetradentate ligand, comprising a *bis-anion-bis*-(NHC carbene) alkylene of the structure:




wherein R_1 - R_8 are independently hydrogen, fluoro, chloro, bromo, iodo, hydroxyl, alkyl, substituted alkyl, cycloalkyl, substituted cycloalkyl, aryl, substituted aryl, acyl, alkoxy, acyloxy, amino, nitro, acylamino, aralkyl, cyano, carboxyl, thio, styryl, aminocarbonyl, carbamoyl, aryloxy carbonyl, phenoxy carbonyl, or alkoxy carbonyl;

wherein at least one of R_1 - R_8 is not hydrogen; and

wherein X is independently O, NR_9 , S, PR_9 , or Se, where R_9 is H or alkyl.

2. The tetradentate ligand of claim 1, wherein R_6 or R_8 is substituted with an electron withdrawing substituent.
3. The tetradentate ligand of claim 1, wherein R_6 is fluoro.
4. A precursor to the tetradentate ligand of claim 1, comprising the structure:




wherein R_1 - R_8 are independently hydrogen, fluoro, chloro, bromo, iodo, hydroxyl, alkyl, substituted alkyl, cycloalkyl, substituted cycloalkyl, aryl, substituted aryl, acyl, alkoxy, acyloxy, amino, nitro, acylamino, aralkyl, cyano, carboxyl, thio, styryl, aminocarbonyl, carbamoyl, aryloxy carbonyl, phenoxy carbonyl, or alkoxy carbonyl;

wherein at least one of R_1 - R_8 is not hydrogen;

wherein X is independently O, NR_9 , S, PR_9 , or Se, where R_9 is H or alky; and


wherein A^- is chloride, bromide, iodide, tosylate, brosylate, triflate, or other anion of low nucleophilicity.

5. The precursor of claim 4, wherein R_6 or R_8 is substituted with an electron withdrawing substituent.
6. The precursor of claim 4, wherein R_6 is fluoro.
7. The precursor of claim 4, wherein A^- is bromide.
8. The precursor of claim 4, wherein the structure is:



10. The precursor of claim 4, wherein H of the XH is replaced with a methyl or other protecting group.

11. A tetradentate *bis*-(NHC carbenes) alkylene ligand Pt(II) complex comprising the ligand of claim 1, comprising the structure:




wherein R_1 - R_8 are independently hydrogen, fluoro, chloro, bromo, iodo, hydroxyl, alkyl, substituted alkyl, cycloalkyl, substituted cycloalkyl, aryl, substituted aryl, acyl, alkoxy, acyloxy, amino, nitro, acylamino, aralkyl, cyano, carboxyl, thio, styryl, aminocarbonyl, carbamoyl, aryloxy carbonyl, phenoxy carbonyl, or alkoxy carbonyl;

wherein at least one of R_1 - R_8 is not hydrogen; and

wherein X is independently O, NR_9 , S, PR_9 , or Se, where R_9 is H or alkyl.

12. The tetradentate *bis*-(NHC carbenes) alkylene ligand Pt(II) complex of claim 11, wherein R_6 or R_8 is substituted with an electron withdrawing substituent.
13. The tetradentate *bis*-(NHC carbenes) alkylene ligand Pt(II) complex of claim 11, wherein R_6 is fluoro.
14. The tetradentate *bis*-(NHC carbenes) alkylene ligand Pt(II) complex of claim 11, wherein the tetradentate ligand Pt(II) complex has a blue emission with a maximum less than 470 nm.
15. The tetradentate *bis*-(NHC carbenes) alkylene ligand Pt(II) complex of claim 14, wherein the tetradentate ligand Pt(II) complex has the blue emission with a quantum efficiency in solution of at least 5 percent.
16. The tetradentate *bis*-(NHC carbenes) alkylene ligand Pt(II) complex of claim 11, of the structure:



17. A method for the preparation of the tetradentate *bis*-(NHC carbenes) alkylene ligand Pt(II) complex of claim 11, comprising combining a precursor of claim 4 with a Pt(II) salt in the presence of a proton acceptor in solution.

18. The method of claim 17, wherein the proton acceptor is a tertiary amine.

19. The method of claim 17, wherein the Pt(II) salt is a Pt(II) halide.

20. The method of claim 17, wherein the Pt(II) halide is Pt(DMSO)₂Cl₂.

21. An organic light-emitting diode (OLED), comprising an electroluminescence layer comprising a tetradentate *bis*-(NHC carbenes) alkylene ligand Pt(II) complex of claim 11.

22. An organic light-emitting diode (OLED) of claim 21, wherein the tetradentate *bis*-(NHC carbenes) alkylene ligand Pt(II) complex has a structureless blue emission in dilute solution having a λ_{\max} less than 470 nm with a quantum yield, ϕ , greater than 5 %.




Figure 1




Figure 2




Figure 3




Figure 4




Figure 5




Figure 6




Figure 7




Figure 8




Figure 9




Figure 10




Figure 11




Figure 12

INTERNATIONAL SEARCH REPORT

International application No.

PCT/CN2012/076252

A. CLASSIFICATION OF SUBJECT MATTER

See extra sheet

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC: C07F, C09K, H05B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI, EPODOC, CNKI, CPRS, STN: phosphor, complex, tetradentate

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	TAKEYOSHI Yagyu <i>et al.</i> , Synthesis and Characterization of a Manganese(III) Complex with a Tetradentate N-Heterocyclic Carbene Ligand, <i>Organometallics</i> , 05 March 2009, Vol. 28, NO. 7, pages 2342-2344, especially page 2343, CODEN: ORGND7; ISSN: 0276-7333	1, 4, 7-8, 10
A		2-3, 5-6, 11-22
A	ANKE Meyer <i>et al.</i> , Platinum(II) Complexes with Tetradentate Dianionic(O ⁻ C ⁻ C ⁻ O ⁻)-Ligands, <i>Organometallics</i> , 09 May 2011, Vol.30, No. 11, pages 2980-2985, especially results and discussion, CODEN: ORGND7; ISSN: 0276-7333	1-8, 10-22
P, X	LI, Kai <i>et al.</i> , Blue Electrophosphorescent Organoplatinum(II) Complexes with Dianionic Tetradentate Bis(carbene) Ligands, 15 July 2011, Vol.47, No. 32, pages 9075-9077, especially column 1-2, CODEN: CHCOFS; ISSN: 1359-7345	1-8, 10-22

Further documents are listed in the continuation of Box C.

See patent family annex.

<p>* Special categories of cited documents:</p> <p>“A” document defining the general state of the art which is not considered to be of particular relevance</p> <p>“E” earlier application or patent but published on or after the international filing date</p> <p>“L” document which may throw doubts on priority claim (S) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>“O” document referring to an oral disclosure, use, exhibition or other means</p> <p>“P” document published prior to the international filing date but later than the priority date claimed</p>	<p>“T” later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>“X” document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>“Y” document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>“&” document member of the same patent family</p>
--	---

Date of the actual completion of the international search
21 June 2012 (21.06.2012)

Date of mailing of the international search report
02 Aug. 2012 (02.08.2012)

Name and mailing address of the ISA/CN
The State Intellectual Property Office, the P.R.China
6 Xitucheng Rd., Jimen Bridge, Haidian District, Beijing, China
100088
Facsimile No. 86-10-62019451

Authorized officer
DI, Yanxin
Telephone No. (86-10)62086319

INTERNATIONAL SEARCH REPORT

International application No.

PCT/CN2012/076252

CLASSIFICATION OF SUBJECT MATTER

C07F 15/00 (2006.01) i

C09K 11/06 (2006.01) i

H05B 33/14 (2006.01) i