

## RESEARCH HIGHLIGHT

## Valley light-emitting transistor


Wang Yao

NPG Asia Materials (2014) 6, e124; doi:10.1038/am.2014.69; published online 12 September 2014

In crystalline solids, it is often the case that the Fermi surface consists of multiple pockets at well-separated degenerate band extrema (that is, valleys) in momentum space. The valley index constitutes a discrete degree of freedom of carrier, just like spin. Exploiting valley in addition to spin will make future electronics more versatile. Two-dimensional (2D) transition metal dichalcogenides, a new class of direct-gap semiconductors,<sup>1,2</sup> have provided an appealing laboratory to explore valley-electronics, because of the discovery of a valley optical selection rule that allows optical control and detection of valley polarization.<sup>3</sup> Iwasa from University of Tokyo, and Riken and his team have now demonstrated in 2D WSe<sub>2</sub> the first electric control of valley-dependent optical emission.<sup>4</sup>

Their device is a forward-biased p-i-n junction (Figure 1a), where electrons and holes flow to the intrinsic region to recombine and emit photons. This electroluminescence is found to have a circular polarization, which changes sign when the p-i-n junction is flipped.<sup>4</sup> By the valley optical selection rule (Figure 1b), the observation implies that the light emission from the two valleys is unbalanced and determined by the electric control, realizing a prototype valley light-emitting transistor.

The valence band edge in 2D WSe<sub>2</sub> has strong trigonal warping that makes the dispersion asymmetric and valley-dependent: in valley K left-moving holes can have larger velocity than right-moving ones, while valley -K has the opposite situation. A large electric field can cause a valley-dependent separation of the electron and hole pockets and hence different light emission rates from the two valleys even in the absence of carrier valley polarization (Figure 1c).<sup>4</sup> The luminescence polarization therefore may be locally induced by the electric field from the built-in potential in the intrinsic region. Alternatively, a valley transport effect can lead to the same observation. Also due to the valley-dependent dispersion, the current driven by the forward bias can have different magnitude in the two valleys,<sup>5</sup> so that carriers injected into the intrinsic region are valley polarized, leading to



**Figure 1** (a) Circularly polarized electroluminescence from a p-i-n junction electrostatically formed in two-dimensional WSe<sub>2</sub> (provided by Iwasa and coworkers<sup>4</sup>). (b) The momentum-conserving interband transitions in valley K (-K) couple to right- (left-) handed circularly polarized light only. Valley polarization of carriers can lead to circularly polarized luminescence. (c) In the absence of valley polarization, circularly polarized luminescence is possible in a large electric field, where the overlap between the electron and hole pockets becomes different in the two valleys due to the valley-dependent dispersions.

circularly polarized luminescence. The unique signature of this valley transport effect is a spatial pattern of the polarization, depending on the orientation of the junction with respect to crystalline axis.<sup>5</sup> Spatial-resolved and polarization-resolved luminescence detection will potentially identify the dominating mechanism in the device.

5 Yu, H., Wu, Y., Liu, G., Xu, X. & Yao, W. Nonlinear valley and spin currents from Fermi pocket anisotropy in 2D crystals. Preprint at <http://arXiv.org/abs/1406.2931> (2014)



This work is licensed under a Creative Commons Attribution-NonCommercial-NoDerivs 3.0 Unported License. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in the credit line; if the material is not included under the Creative Commons license, users will need to obtain permission from the license holder to reproduce the material. To view a copy of this license, visit <http://creativecommons.org/licenses/by-nc-nd/3.0/>

- 1 Mak, K. F., Lee, C., Hone, J., Shan, J. & Heinz, T. F. Atomically thin MoS<sub>2</sub>: a new direct-gap semiconductor. *Phys. Rev. Lett.* **105**, 136805 (2010).
- 2 Splendiani, A., Sun, L., Zhang, Y., Li, T., Kim, J., Chin, C.-Y., Galli, G. & Wang, F. Emerging photoluminescence in monolayer MoS<sub>2</sub>. *Nano. Lett.* **10**, 1271–1275 (2010).
- 3 Xiao, D., Liu, G.-B., Feng, W., Xu, X. & Yao, W. Coupled spin and valley physics in monolayers of MoS<sub>2</sub> and other group VI dichalcogenides. *Phys. Rev. Lett.* **108**, 196802 (2012).
- 4 Zhang, Y. J., Oka, T., Suzuki, R., Ye, J. T. & Iwasa, Y. Electrically switchable chiral light-emitting transistor. *Science* **344**, 725–728 (2014).